


GIPPSLAND PREMIUM QUARRIES PTY LTD

Phone: 5626 6499
Fax: 5626 6491

COARSE WASHED SAND

DATE: 04/07/17 TIME 2.40 PM	SAND TYF COARSE WASHED SAND
SAMPLE FROM: SALES	MASS SAMPLED: 600 TONNE



SIEVE	PAN	75	150	300	600	1.18	2.36	4.75
WEIGHT RETAINED	432.8	431.36	423.6	385.8	312.9	219.8	95.9	10
UPPER LIMIT		10	20	50	90	100	100	100
% PASSING		0.27	2.26	10.85	27.70	49.21	77.84	97.68
LOWER LIMIT		0	0	8	20	40	60	90

SAND ANALYSIS APPLICABLE TO THE PRODUCTION OF	COARSE WASHED SAND
WASHED / GRADING	
LAB TECHNICIAN	BARRY DICKESON
ADDITIONAL COMMENTS	

MOISTURE CONTENT (AS 1289.2.1.1)	CLAY FINE SILT (AS 1141.3.3)
WET MASS <u>850</u> DRY MASS <u>811.2</u>	SAND _____ SILT _____
MC=(WM-DM/DM X 100) <u>4.78%</u>	C=(SILT/SAND) X 10(<u>#DIV/0!</u>)
MOISTURE CONTENT = 4% - 6%	SILT CONTENT = 6% - 8%