


# GIPPSLAND PREMIUM QUARRIES PTY LTD

Phone: 5626 6499  
Fax: 5626 6491

## COARSE WASHED SAND

DATE: 08/03/18 TIME 8.30 AM	SAND TYF COARSE WASHED SAND
SAMPLE FROM: SALES	MASS SAMPLED: 600 TONNE



SIEVE	PAN	75	150	300	600	1.18	2.36	4.75
WEIGHT RETAINED	406.3	405.5	394	361.5	306.7	229.3	115	18.7
<b>UPPER LIMIT</b>		10	20	50	90	100	100	100
<b>% PASSING</b>		0.19	3.02	11.02	24.51	43.56	71.69	95.39
<b>LOWER LIMIT</b>		0	0	8	20	40	60	90

SAND ANALYSIS APPLICABLE TO THE PRODUCTION OF	COARSE WASHED SAND
WASHED / GRADING	
LAB TECHNICIAN	BARRY DICKESON
ADDITIONAL COMMENTS	

MOISTURE CONTENT (AS 1289.2.1.1)	CLAY FINE SILT (AS 1141.3.3)
WET MASS <u>850</u> DRY MASS <u>814.1</u>	SAND _____ SILT _____
MC=(WM-DM/DM X 100) <u>4.41%</u>	C=(SILT/SAND) X 10( <u>#DIV/0!</u> )
MOISTURE CONTENT = 4% - 6%	SILT CONTENT = 6% - 8%